HAYES MICROBIAL CONSULTING

#25031723

Analysis Report prepared for

PuroClean of South Reno

1550 Glendale Ave.
Sparks, NV 89431

Phone: **(775) 446-4646**

5835 Ingleston Dr.

Collected: **July 15, 2025**
Received: **July 17, 2025**
Reported: **July 17, 2025**

We would like to thank you for trusting Hayes Microbial for your analytical needs!
We received 3 samples by FedEx in good condition for this project on July 17th, 2025.

The results in this analysis pertain only to this job, collected on the stated date, and should not be used in the interpretation of any other job. Information supplied by the customer can affect the validity of results. These results apply only to the samples as received. This report may not be duplicated, except in full, without the written consent of Hayes Microbial Consulting, LLC.

All information provided to Hayes Microbial is confidential information relating to our customers and their clients. We will not disclose, copy, or distribute any information verbally or written, except to those designated by the customer(s). We take confidentiality very seriously. No changes to the distribution list will be made without the express consent of the customer.

This laboratory bears no responsibility for sample collection activities, analytical method limitations, or your use of the test results. Interpretation and use of test results are your responsibility. Any reference to health effects or interpretation of mold levels is strictly the opinion of Hayes Microbial. In no event, shall Hayes Microbial or any of its employees be liable for lost profits or any special, incidental or consequential damages arising out of the use of these test results.

Steve Hayes, BSMT(ASCP)
Laboratory Director
Hayes Microbial Consulting, LLC.

EPA Laboratory ID: VA01419

DPH License: #PH-0198

Shaun Mihaila
PuroClean of South Reno
1550 Glendale Ave.
Sparks, NV 89431
(775) 446-4646

5835 Ingleston Dr.

#25031723

Asbestos PLM Bulk

EPA 600/R-93/116; EPA 40 CFR Appendix E to Subpart E of Part 763

#	Sample	Material Description	Non-Fibrous	Non-Asbestos Fibers	Asbestos Fibers
1	1 - DW, JC, Tex - Bedroom Closet Level 2, SE Wall	Homogenous / Texture / Off-White	100%		**None Detected**
		Homogenous / Tape / Cream	2%	98% Cellulose Fibers	**None Detected**
		Homogenous / Joint Compound / White	100%		**None Detected**
		Heterogenous / Drywall / White	95%	5% Cellulose Fibers	**None Detected**
2	2 - DW, JC, Tex - Bedroom Closet Level 2, NW Wall	Homogenous / Texture / Off-White	100%		**None Detected**
		Homogenous / Tape / Cream	2%	98% Cellulose Fibers	**None Detected**
		Homogenous / Joint Compound / White	100%		**None Detected**
		Heterogenous / Drywall / White	95%	5% Cellulose Fibers	**None Detected**

Shaun Mihaila
PuroClean of South Reno
1550 Glendale Ave.
Sparks, NV 89431
(775) 446-4646

5835 Ingleston Dr.

#25031723

Asbestos PLM Bulk

EPA 600/R-93/116; EPA 40 CFR Appendix E to Subpart E of Part 763

#	Sample	Material Description	Non-Fibrous	Non-Asbestos Fibers	Asbestos Fibers
3	3 - DW, JC, Tex - Toilet Room Level 2, SW Wall	Homogenous / Texture / Off-White	100%		**None Detected**
		Homogenous / Tape / Cream	2%	98% Cellulose Fibers	**None Detected**
		Homogenous / Joint Compound / White	100%		**None Detected**
		Heterogenous / Drywall / White	95%	5% Cellulose Fibers	**None Detected**

Shaun Mihaila
PuroClean of South Reno
1550 Glendale Ave.
Sparks, NV 89431
(775) 446-4646

5835 Ingleston Dr.

#25031723

Asbestos Analysis Information

Analysis Details	All samples were received in acceptable condition unless otherwise noted on the report. This report must not be used by the client to claim product certification, approval, or endorsement by AIHA, NIST, NVLAP, NY ELAP, or any agency. The results relate only to the items tested. Hayes Microbial Consulting reserves the right to dispose of all samples after a period of 60 days in compliance with state and federal guidelines.
PLM Analysis	All Polarized Light Microscopy (PLM) results include an inherent uncertainty of measurement associated with estimating percentages by PLM. Materials with interfering matrix, low asbestos content, or small fiber size may require additional analysis via TEM Analysis.
TEM Analysis	Analysis by TEM is capable of providing positive identification of asbestos type(s) and semi-quantitation of asbestos content.
Definitions	'None Detected' - Below the detected reporting limit of 1% unless point counting is performed, then the detected reporting limit is .25%.
New York ELAP	Per NY ELAP198.6 (NOB), TEM is the only reliable method to declare an NOB material as Non-Asbestos Containing. Any NY ELAP samples that are subcontracted to another laboratory will display the name and ELAP Lab Identification number in the report page heading of those samples. The original report provided to Hayes Microbial Consulting is available upon request.